

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 254 867 A2**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
06.11.2002 Bulletin 2002/45

(51) Int Cl.7: **C03B 37/014, C03B 19/14**

(21) Application number: **02078244.7**

(22) Date of filing: **19.12.1995**

(84) Designated Contracting States:
DE FR GB IT NL

(30) Priority: **30.12.1994 US 367047**

(62) Document number(s) of the earlier application(s) in
accordance with Art. 76 EPC:
99203799.4 / 0 978 491
95944371.4 / 0 800 490

(71) Applicant: **Corning Incorporated**
Corning, New York 14831 (US)

(72) Inventors:
• **Cain, Michael B.**
Corning, NY 14831 (US)

• **Desorcie, Robert B.**
Corning, NY 14831 (US)
• **Kiefer, William J.**
Horseheads, NY 14845 (US)
• **Powers, Dale R.**
Painted Post, NY 14870 (US)

(74) Representative: **Marchant, James Ian et al**
Elkington and Fife,
Prospect House,
8 Pembroke Road
Sevenoaks, Kent TN13 1XR (GB)


Remarks:

This application was filed on 06 - 08 - 2002 as a
divisional application to the application mentioned
under INID code 62.

(54) **Apparatus comprising a burner for producing silicon dioxide soot**

(57) A precision burner for oxidizing halide-free, silicon-containing compounds, such as octamethylcyclotetrasiloxane (OMCTS), is provided. The burner includes a subassembly (13) which can be precisely mounted on a burner mounting block (107) through the use of an alignment stub (158), a raised face (162) on the burner mounting block (107) and corresponding recess (160) in the back of the subassembly (13). The burner's face includes four concentric gas-emitting regions: a first central region (36, 90) from which exits a mixture of OMCTS and O_2 , a second innershield region (38, 92) from which exits N_2 , a third outershield region (40, 42, 94, 96) from which exits O_2 , and a fourth premix region (44, 98) from which exits a mixture of CH_4 and O_2 . The burner provides more efficient use of halide-free silicon-containing raw materials than prior art burners.

FIG. 4.



Description

FIELD OF THE INVENTION

5 [0001] This invention relates to burners for use in producing preforms from which optical waveguide fibers are drawn.

BACKGROUND OF THE INVENTION

10 [0002] Historically, halide-containing raw materials, such as, SiCl_4 or mixtures of SiCl_4 with various dopants, have been used in the manufacture of preforms by vapor phase deposition techniques, such as, the VAD (vapor axial deposition) and OVD (outside vapor deposition) techniques.

[0003] In these procedures, the halide-containing raw materials are volatilized and then hydrolyzed in a burner to produce soot particles which are collected on a rotating starting rod (bait tube) in the case of VAD or a rotating mandrel in the case of OVD. In some OVD systems, the cladding portion of the preform is deposited on a previously-formed
15 core preform, rather than on a mandrel.

[0004] Numerous burner designs have been developed for use in such processes, examples of which can be found in Moltzan et al., U.S. Patent No. 3,642,521, Powers, U.S. Patent No. 4,165,223, Moltzan, U.S. Patent No. 3,565,345, and Moltzan, U.S. Patent No. 3,698,936.

20 [0005] In particular, Suda et al., U.S. Patent No. 4,801,322, discuss the problem of soot particles adhering to the orifices of a burner (see column 12, lines 55-66); Kawachi et al., U.S. Patent No. 4,406,684, and Watanabe et al., U.S. Patent No. 4,915,717, disclose burners in which an outlet for a raw material is surrounded by an outlet for an inert gas; and Andrejco et al., U.S. Patent No. 4,474,593, disclose a burner employing concentric tubes, some of which have machined splines on their outer surfaces.

25 [0006] The use of halide-containing raw materials generates substantial quantities of halide-containing by-products, e.g., hydrochloric acid. To avoid environmental pollution, these by-products must be collected, which increases the overall cost of the preform production process. Accordingly, halide-free materials and, in particular, halide-free, silicon-containing materials are desirable starting materials for the production of optical waveguide preforms. See Dobbins et al., U.S. Patent No. 5,043,002.

30 [0007] As explained in the Dobbins et al. patent, the relevant portions of which are incorporated herein by reference, particularly preferred halide-free, silicon-containing materials for use in producing optical waveguide preforms are polymethylsiloxanes, with the polymethylcyclsiloxanes being particularly preferred, and with octamethylcyclotetrasiloxane (OMCTS) being especially preferred. These same halide-free, silicon-containing raw materials are preferred for use with the present invention.

35 [0008] Although conventional burners can be used to oxidize halide-free, silicon-containing materials, such burners, having been designed for use with halide-containing raw materials, do not achieve particularly efficient utilization of halide-free materials. These deficits arise both from the burner's construction and from the exit locations at the burner's face of the various gases used in the oxidization process. As discussed in detail below, in accordance with the present invention, gas flow patterns and burner configurations have been developed which eliminate these deficits.

40 [0009] In the OVD process, preforms can be made by traversing a single burner along the entire length of the preform or by using a series of burners mounted on an oscillating manifold, with each burner traversing only a portion of the preform. In the latter case, the uniformity of the burners relative to one another determines the longitudinal uniformity of the preform.

45 [0010] Prior art burners have often exhibited substantial variability in their properties which, in turn, has resulted in an undesirable level of variability in preforms produced using such burners in an oscillating manifold. As detailed below, as a further aspect of the invention, burner configurations have been developed which minimize this burner variation.

SUMMARY OF THE INVENTION

50 [0011] In view of the foregoing, it is an object of the present invention to provide burners which will effectively and efficiently oxidize halide-free, silicon-containing raw materials, such as OMCTS.

[0012] It is a further object of the invention to provide a burner construction which allows the burner to be assembled from its component parts and to be mounted on a manifold with a low degree of variability, i.e., to provide a high precision burner.

55 [0013] To achieve the foregoing and other objects, the invention in accordance with certain of its aspects provides a method for forming a preform comprising:

- (a) providing an elongated cylindrical starting member, e.g., a rotating mandrel or a core preform;
- (b) providing a soot-producing burner (10, 100) having a burner face (34, 88) that comprises first (36, 90), second

(38, 92), third (40, 42, 94, 96), and fourth (44, 98) gas-emitting regions, the second region surrounding the first region, the third region surrounding the second region, and the fourth region surrounding the third region;
 (c) providing a mixture comprising oxygen and a halide-free, silicon-containing material, e.g., OMCTS, to the first region;
 (d) providing an inert gas, e.g., N₂, to the second region in an amount sufficient to inhibit the burner's soot stream from touching down on the burner's face;
 (e) providing oxygen to the third region;
 (f) providing a mixture comprising oxygen and a combustible gas, e.g., CH₄, to the fourth region; and
 (g) depositing glass soot on the starting member to form the preform by producing relative oscillatory motion between the soot-producing burner and the starting member.

[0014] In accordance with others of its aspects, the invention provides a soot-producing burner comprising:

(a) a burner subassembly (13) which comprises:

a back block (106) having a plurality of gas-carrying passages (112, 114, 116, 126, 128, 130),
 a face block (102) having a central gas-carrying passage (184) and a plurality of gas-carrying passages (186, 188) surrounding the central gas-carrying passage (note that as seen from the burner's face, the central passage is bore 90; however, this bore is formed in tube 108, rather than in face block 102),
 a manifold plate (104) between the back block (106) and the face block (102), which includes a plurality of orifices (170, 172) for providing circumferential equalization of the pressure of gas flowing through the plurality of gas-carrying passages (186, 188) surrounding the central gas-carrying passage (184) of the face block (102), and
 means (105, 150, 152, 154, 156) for forming an assembly (13) of the face block (102), back block (106), and manifold plate (104);

(b) a burner subassembly mounting block (107) for attachment to a gas-supplying manifold; and

(c) means (140, 142, 144, 158, 160, 162) for precisely mounting the burner subassembly 13 on the burner subassembly mounting block (107).

[0015] In certain preferred embodiments, the burner includes a fume tube (108) having an integral manifold (110) which includes a plurality of orifices (168) for providing circumferential equalization of the pressure of gas flowing through central gas-carrying passage (184) of the face block (102). In other preferred embodiments, the manifold plate (104) includes a flange (105) for providing a precise alignment between the face block (102), back block (106), and manifold plate (104) in the assembled burner.

PRIEF DESCRIPTION OF THE DRAWINGS

[0016] Figure 1 is an exploded view of a prior art burner.

[0017] Figure 2 is a schematic diagram of a gas delivery system for use in the practice of the present invention.

[0018] Figure 3 is a plan view of the burner face of the burner of Figure 1. The indicated gas flows on this figure are those of the present invention.

[0019] Figure 4 is a plan view of a burner face constructed in accordance with the present invention. As in Figure 3, the gas flows shown are those of the present invention.

[0020] Figure 5 is an exploded view of a precision burner constructed in accordance with the present invention.

[0021] Figure 6 is a cross-sectional view of the precision burner of the invention along lines 6-6 in Figure 5.

[0022] Figure 7 is a cross-sectional view along lines 7-7 in Figure 5 of the back block component of the precision burner of the invention.

[0023] The foregoing drawings, which are incorporated in and constitute part of the specification, illustrate the preferred embodiments of the invention, and together with the description, serve to explain the principles of the invention. It is to be understood, of course, that both the drawings and the description are explanatory only and are not restrictive of the invention.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0024] As discussed above, one of the aspects of the present invention is the arrangement of the various gas flows at the burner face. Such gas flows can be implemented using a prior art burner construction or preferably using the improved burner constructions disclosed herein.

[0025] Figure 1 shows a prior art burner 10 of the type previously used in the OVD process to produce preforms. Burner 10 includes face block 12, manifold plate 14, back block 16, fume tube 18, and inner shield manifold 20. Manifold plate 14 includes annularly arranged orifices 46 for providing uniform gas flows at burner face 34. O-rings 50 are received in grooves 48 of manifold plate 14 and serve to prevent gas leakage between the various passages of the burner. Fume tube 18, which is threaded at its rear end, extends through back block 16 and carries inner shield manifold 20 at its leading end. In particular, in the assembled burner, inner shield manifold 20 abuts shoulder 52 of fume tube 18.

[0026] Burner 10 is assembled by screwing fume tube 18 into the back of central aperture 22 of back block 16, the rear portion of the aperture being threaded for this purpose, inserting O-rings 50 in grooves 48 of manifold plate 14, passing the manifold plate over the leading end of the fume tube and aligning bolt holes 26 in the plate with bolt holes 24 in the back block, sliding inner shield manifold 20 onto the fume tube, and passing face block 12 over the leading end of the fume tube and aligning its bolt holes 28 with bolt holes 26. Bolts 30, only one of which is shown in Figure 1, are then inserted through aligned bolt holes 24, 26, and 28, and tightened to hold burner 10 together. The assembled burner is then mounted on a gas-supplying manifold, e.g., a multi-burner, oscillating manifold, by means of mounting flange 32 on back block 16. The gas-supplying manifold provides the various gases used by the burner by means of gas supply lines and gas tight fittings which mate with gas-receiving apertures (not shown) in the back surface of back block 16.

[0027] In practice, it has been found that the positioning of inner shield manifold 20 on fume tube 18 and the alignment of face block 12, manifold plate 14, back block 16, and fume tube 18 has varied from burner to burner. Also, the use of flanges 32 to mount a series of burners on a multi-burner, gas-supplying manifold has resulted in variations in the locations of the burners relative to the axis of the preform being produced. Both of these variations are addressed by precision burner 100 shown in Figures 5-7 and discussed below.

[0028] Figure 3 is a plan view of face 34 of burner 10. As can be seen in this view, the burner face contains a series of annular regions 36 through 44 through which the various gases and gas mixtures used in producing soot particles pass. Region 36 comprises the bore of fume tube 18, while region 38 comprises the space between the fume tube and the central bore 53 of face block 12. The remaining regions 40, 42, and 44 are each composed of multiple orifices, although continuous open rings, like that of region 38, can be used for these regions in the practice of the invention, if desired. Fume tube 18 can be recessed behind face 34 of face block 12 by, for example, about 2 millimeters.

[0029] When used in prior art processes employing halide-containing raw materials, regions 36 through 44 carried the following gases:

Table 1

region 36	halide containing raw material/inert gas mixture
region 38	oxygen
region 40	combustible gas/oxygen mixture
region 42	combustible gas/oxygen mixture
region 44	oxygen

[0030] In accordance with the invention, it has been found that the regions should carry the following gases when halide-free, silicon-containing materials, such as OMCTS, are to be oxidized:

Table 2

region 36	halide-free, silicon-containing raw material/oxygen mixture plus, optionally, inert gas
region 38	inert gas, e.g., nitrogen and/or argon
region 40	oxygen
region 42	oxygen
region 44	combustible gas/oxygen mixture

[0031] This arrangement of gas flows is shown in Figure 3 for a system in which the halide-free, silicon-containing raw material is OMCTS, the inert gas is nitrogen, and the combustible gas is methane (CH_4).

[0032] Figure 2 schematically illustrates a delivery system for these gases comprising regulated gas sources 54 through 62, burner feed lines 64 through 70, gas mixers 72 and 74, and metering pump 76, flowmeter 78, preheater 80, regulator 82, vaporizer 84, and valve 86 for vaporizing and dispensing OMCTS. Various equipment known to those skilled in the art can be used in the construction of the delivery system of Figure 2. For example, Cain et al., U.S. Patent No. 5,356,451, discloses suitable equipment for use in vaporizing and dispensing OMCTS. Other equipment and delivery systems can, of course, be used in the practice of the invention.

[0033] In both Figures 2 and 3, as well as in Figure 4, "fume" designates oxygen supplied to region 36, "innershield"

designates nitrogen supplied to region 38, "outershield" designates oxygen supplied to regions 40 and 42, and "premix" designates the methane/oxygen mixture supplied to region 44. Note that regions 40 and 42 can be considered subregions of a single region since they carry the same gas.

[0034] The gas flow pattern shown in Figure 3 and set forth above in Table 2 provides for more efficient utilization of halide-free, silicon-containing raw materials, such as OMCTS, than that achieved with the prior art pattern of Table 1. In particular, in accordance with the invention, it has been determined that compounds such as OMCTS require a large amount of oxygen to completely react and little external heat since the compound contains a large amount of fuel in its own composition.

[0035] The use of regions 40 and 42 to supply oxygen, rather than a combustible gas/oxygen mixture, as in the gas flow pattern of Table 1 provides a high volume of oxygen at a position close to the fume tube sufficient to fully react OMCTS and similar compounds. Moreover, limiting the combustible gas/oxygen mixture to region 44 has been found to provide sufficient external heat for the oxidation process, while at the same time reducing the amount of combustible gas required for preform production.

[0036] Significantly it has been found that oxygen needs to be removed from region 38, i.e., the innershield, when oxidizing halide-free compounds such as OMCTS. If oxygen is used in this region, the soot stream has a tendency to touch down on the burner face and deposit silica around fume tube 18. Passing an inert gas, such as nitrogen, through the innershield moves the reaction between the halide-free compound and oxygen to a point sufficiently far from the burner face to prevent soot deposition on the fume tube.

[0037] Preferred feed/flow rates for the various materials/gases of Table 2 are as follows for the burner construction of Figure 1 and the burner face configuration of Figure 3: OMCTS - 13 grams/minute; fume O_2 - 5 slpm (standard liters per minute); fume N_2 (optional) - 0.4 slpm; innershield N_2 - 3.8 slpm; outershield O_2 - 7 slpm; premix CH_4 - 3.5 slpm; and premix O_2 - 2.8 slpm.

[0038] In practice, it has been found that deposition rate and collection efficiency are most dependent upon OMCTS feed rate, fume O_2 flowrate, and target diameter, while soot preform density is most dependent upon total oxygen content (fume O_2 flowrate and outershield O_2 flowrate), target diameter, and burner to target distance. These parameters can thus be varied to optimize deposition rate, collection efficiency, and preform density using process control procedures known to persons skilled in the art.

[0039] The lack of a significant dependence of soot density on OMCTS feed rate means that soot density can be controlled independently of deposition rate. Specifically, soot density can be optimized to achieve a constant radial density profile and then the deposition rate can be optimized using the OMCTS feed rate without disturbing the constant radial density profile. In terms of commercial production, this is an important advantage of the gas flow patterns of the present invention.

[0040] Figure 4 illustrates an improved burner face construction for use in oxidizing halide-free, silicon containing raw materials. A comparison of Figures 3 and 4 reveals the following differences between burner face 88 of Figure 4 and burner face 34 of Figure 3:

(1) The number of orifices in region 98 of burner face 88 is half the number of region 44 of burner face 34. This causes the $CH_4 + O_2$ premix flame to extend further away from the burner face and thus be more stable and less prone to flash back. It also results in a significant reduction in the burner's operating temperature (e.g., from about 350-400°C to about 200-250°C) which, in turn, results in a significantly longer life for the burner's O-ring seals.

(2) Regions 94 and 96 of burner face 88 are closer to region 92 than the corresponding regions of face 34 so as to reduce the diffusion distance for oxygen from outershield regions 94 and 96 to fume tube region 90. Preferred diameters for regions 94, 96 and 98 are 7.9, 11.9, and 17.0 mm, respectively, while those for regions 40, 42, and 44 are 8.4, 13.5, and 18.0 mm, respectively. If the diameters of regions 94, 96, and 98 are designated D_i , D_o , and D_4 , respectively, then it can be seen in Figure 4 that $D_4 - D_c$ is greater than $D_o - D_i$.

[0041] In addition to the foregoing changes, the focus angle, i.e., the angle which the centerline of an orifice makes with a normal to the face of the burner, was increased from 13° for the orifices of burner face 34 to 16° for the orifices of face 88. Also, while the orifices of regions 40, 42, and 44 of burner face 34 are all of the same size (e.g., 0.09 mm), the orifices of regions 94 and 96 of burner face 88 are approximately 1/3 larger than the orifices of region 98 (e.g., 0.12 mm for regions 94 and 96 versus 0.09 mm for region 98). This increase in diameter reduces the velocity of the oxygen exiting these regions and thus keeps the oxygen flows from tearing the flame apart. Further, the diameter of region 92 is somewhat smaller than the diameter of region 38 (e.g., 4.1 mm diameter for region 92 versus 4.6 mm diameter for region 38) so as to reduce to some extent the flow of innershield nitrogen.

[0042] Preferred feed/flow rates for the various materials/gases of Table 2 are as follows for the burner construction of Figure 1 and the burner face configuration of Figure 4: OMCTS - 12.5 grams/minute (region 90); fume O_2 - 5.5 slpm (region 90); fume N_2 (optional) - 0.0 slpm (region 90); innershield N_2 - 3.2 slpm (region 92); outershield O_2 - 9.9 slpm (regions 94 and 96); premix CH_4 - 3.5 slpm (region 98); and premix O_2 - 2.8 slpm (region 98).

[0043] Deposition rate, collection efficiency, and soot preform density were found to depend upon the same parameters discussed above in connection with burner face 34, although the dependence of deposition rate and collection efficiency on OMCTS feed rate for burner face 88 was about half that of burner face 34 and burner to target distance was found to play a more important role in deposition rate and collection efficiency for burner face 88. As with burner face 34, soot density did not show a significant dependence on OMCTS feed rate for burner face 88, thus allowing soot density to be controlled independently of deposition rate.

[0044] Testing of burner face 88 showed that it provided a dramatic increase in deposition rate for small target sizes in comparison to the rate achieved with burner face 34, i.e., a 70% increase at a 7 mm target size (diameter). The amount of increase was less as the target size increased, but was still significant, i.e., at a target size of 54 mm, the increase was estimated to be about 35%. Overall, the average deposition rate increase was approximately 25% for a target that was 0.7 meters long and had an initial diameter of 7 mm, i.e., 5.94 gm/minute for burner face 34 versus 7.41 gm/minute for burner face 88 for a fixed density of 0.6 gm/cm³. Significantly, the increase in deposition rate was achieved without a loss in preform density.

[0045] Figures 5-7 illustrate a preferred burner construction for use with a multi-burner, gas-supplying manifold. In particular, burner 100 shown in these figures can be assembled and mounted on a gas-supplying manifold with a high degree of precision. The burner is thus particularly well-suited for use in OVD systems wherein multiple burners are employed in the production of preforms, with each burner depositing soot on only a portion of the preform.

[0046] Although particularly advantageous for such multi-burner applications, precision burner 100 can be used in single burner applications, if desired. Similarly, although the preferred application of the burner is in the oxidation of halide-free, silicon-containing raw materials, the burner can also be used with halide-containing materials. In such a case, a gas flow pattern like that of Table 1 and a burner face configuration like that of Figure 3 will normally be used. For the purposes of the following discussion, it is assumed that the burner is used with halide-free, silicon-containing raw materials and thus has the gas flow pattern and burner face configuration of Figure 4.

[0047] Precision burner 100 has five main components: face block 102, manifold plate 104, back block 106, fume tube 108, and burner mounting block 107.

[0048] In use, face block 102, manifold plate 104, back block 106, and fume tube 108 are assembled as described below to form subassembly 13, burner mounting block 107 is mounted on a gas-supplying manifold (not shown) by means of bolts 148 which pass through unthreaded bolt holes 146 in burner mounting block 107 and engage corresponding threaded bolt holes in the gas-supplying manifold, and then subassembly 13 is mounted on burner mounting block 107 by means of bolts 144 which pass through unthreaded bolt holes 140 in back block 106 and engage threaded bolt holes 142 in burner mounting block 107. The use of bolts 148 to mount burner block 107 on the gas-supplying manifold, as opposed to flange 32 of prior art burner 10, provides improved repeatability in the mounting of an individual burner and reduced inter-burner variability in the mounting of a series of burners.

[0049] Precision mounting of subassembly 13 on burner mounting block 107 is achieved by means of (1) alignment stud 158 which is carried by burner mounting block 107 and engages an aperture (not shown) in the back of back block 106, and (2) raised face 162 of burner mounting block 107 which is received in recess 160 of back block 106 (see Figure 7). Raised face 162 and recess 160 are preferably machined into their respective blocks to insure a precision fit, e.g., these features are formed by turning of the blocks. These blocks, as well as face block 102 and manifold plate 104 are preferably made of aluminum, which can be readily machined. Fume tube 108 is preferably made of stainless steel, e.g., 303 stainless steel. Other materials can, of course, be used for these components, if desired.

[0050] O-rings 166, only one of which is shown in Figure 5, are used to seal gas receiving apertures 118 through 124 in burner mounting block 107 to their corresponding gas passages in back block 106. At their rearward ends, gas receiving apertures 118 through 124 mate with gas supply lines and gas tight fittings (not shown) provided by the gas-supplying manifold. In terms of the gas flow pattern of Figure 4, gas receiving aperture 118 receives CH₄ + O₂ premix, gas receiving aperture 120 receives OMCTS + fume O₂, gas receiving aperture 122 receives innershield N₂, and gas receiving aperture 124 receives outershield O₂.

[0051] The gas flows through the burner are schematically illustrated by arrows 132 through 138, where arrow 132 represents the flow of OMCTS + fume O₂, arrow 134 represents the flow of innershield N₂, arrow 136 represents the flow of outershield O₂, and arrow 138 represents the flow of CH₄ + O₂ premix. As can be seen in the figures, large gas passages are used in all parts of the burner up to the burner face to reduce the differences in pressure drops between burners.

[0052] As indicated by arrow 132, OMCTS + fume O₂ enters burner mounting block 107 through gas receiving aperture 120, proceeds through fume tube 108, and ultimately exits the burner's face through region 90. Fume tube 108 has a single diameter bored hole 90 for uniform pressure drop and is press fit into back block 106 until it reaches shoulder 176. In this way, a precision alignment is achieved between the fume tube and the back block.

Burner face block 102 has a slide fit over fume tube 108 which provides alignment, as well as easy disassembly, of these components. The bored hole 90 of fume tube 108 preferably has a diameter of, for example, 2.2 mm.

[0053] Orifices 168, which serve to equalize the pressure of the innershield gas, are formed as an integral part of

fume tube 108. They thus form integral inner shield manifold 110 (see Figure 5). This is an important feature of precision burner 100 since it eliminates removable inner shield manifold 20 which was a source of substantial burner-to-burner variability for prior art burner 10.

[0054] Innershield N_2 enters burner mounting block 107 through gas receiving aperture 122 (Figure 5), proceeds through gas passage 126 in back block 106 and into central aperture 112 of that block (see arrow 134 in Figure 7), passes through integral inner shield manifold 110, and ultimately exits the burner's face through region 92. As shown in Figure 7, passage 180 proceeds radially through back block 106 and serves to connect passage 126 with central aperture 112. Passage 180 is sealed at its outer end by a Lee plug.

[0055] Outershield O_2 enters burner mounting block 107 through gas receiving aperture 124 (Figure 5), proceeds through gas passage 128 in back block 106 and into inner annulus 114 of that block (see arrow 136 in Figure 7), passes through pressure equalizing orifices 170 of manifold plate 104, and ultimately exits the burner's face through regions 94 and 96. As shown in Figure 7, passage 182 proceeds radially through back block 106 and serves to connect passage 128 with inner annulus 114. Passage 182 is sealed at its outer end by a Lee plug.

[0056] The $CH_4 + O_2$ premix enters burner mounting block 107 through gas receiving aperture 118 (Figure 6), proceeds through gas passage 130 in back block 106 and into outer annulus 116 of that block (see arrow 138 in Figure 6), passes through pressure equalizing orifices 172 of manifold plate 104, and ultimately exits the burner's face through region 98.

[0057] Subassembly 13 is assembled by press fitting fume tube 108 into central aperture 112 of back block 106, inserting O-rings 164 into grooves 174 of manifold plate 104, passing the manifold plate over the leading end of the fume tube and aligning bolt holes 152 in the plate with bolt holes 150 in the back block, and passing face block 102 over the leading end of the fume tube and aligning its bolt holes 154 with bolt holes 152. Bolts 156, only one of which is shown in Figure 5, are then inserted through aligned bolt holes 150, 152, and 154, and tightened to hold burner subassembly 13 together. The tightening of bolts 156 bring O-rings 164 of manifold plate 104 into engagement with back block 106 and face block 102, thus preventing gas leakage between the various passages of the burner. If desired, a thermocouple may then be mounted in bore 178 in face block 102 (Figure 6).

[0058] The press fitting of fume tube 108 into back block 106 has been found to result in substantially less burner-to-burner variability than that seen with the threaded approach for attaching the fume tube used in prior art burner 10. Also, the rear portion of fume tube 108 comprises a central bore meeting a flat surface. The rear portion of fume tube 18 of prior art burner 10, on the other hand, had a large bore for receiving a gas fitting which tapered down to a smaller bore for carrying fume gases to the burner's face. In practice, it was found that the tapered area varied from piece-to-piece, leading to an overall increase in burner-to-burner variability.

[0059] Manifold plate 104 includes flange 105 which serves the important function of accurately aligning face block 102 and back block 106 with one another and with the manifold plate. The burner-to-burner variability seen in prior art burner 10 is substantially reduced through the use of this flanged plate.

[0060] Without limitation, the following are examples of embodiments of the invention.

[0061] A method of forming a silicon dioxide containing preform comprising the steps of: providing a starting member; providing a soot-producing burner having a burner face that comprises first, second, third, and fourth gas-emitting regions, the second region surrounding the first region, the third region surrounding the second region, and the fourth region surrounding the third region; providing a mixture comprising oxygen and a halide-free, silicon-containing material to the first region; providing an inert gas to the second region in an amount sufficient to inhibit soot from contacting the burner's face; providing oxygen to the third region; providing a mixture comprising oxygen and a combustible gas to the fourth region; depositing silicon dioxide containing soot on the starting member to form the preform by producing relative motion between the soot-producing burner and the starting member, wherein the third gas-emitting region comprises an inner gas-emitting subregion and an outer gas-emitting subregion, wherein the outer gas-emitting subregion of the third gas-emitting region surrounds the inner gas-emitting subregion of the third gas-emitting region, and wherein oxygen is provided to each of the inner and outer gas-emitting subregions of the third gas-emitting region and preferably wherein each of (i) the inner gas-emitting subregion, (ii) the outer gas-emitting subregion, and (iii) the fourth gas-emitting region comprises a ring of orifices, said rings having diameters D_1 , D_0 , and D_4 , respectively, with the difference between D_4 and D_0 being greater than the difference between D_0 and D_1 . The inventive method further comprises a method wherein each of (i) the inner gas-emitting subregion, (ii) the outer gas-emitting subregion, and (iii) the fourth gas-emitting region comprises a ring of orifices, the number of orifices of the fourth gas-emitting region being less than the number of orifices of each of the inner and outer gas-emitting subregions.

[0062] The inventive method further comprises a method wherein each of (i) the inner gas-emitting subregion, (ii) the outer gas-emitting subregion, and (iii) the fourth gas-emitting region comprises a ring of orifices having diameters, the diameter of the orifices of the inner gas-emitting subregion being (a) substantially equal to the diameter of the orifices of the outer gas-emitting subregion and (b) greater than the diameter of the orifices of the fourth gas-emitting region.

[0063] The inventive method further comprises a method wherein each of (i) the inner gas-emitting subregion, (ii) the outer gas-emitting subregion, and (iii) the fourth gas-emitting region comprises a ring of orifices having diameters, said rings having diameters D_i , D_o , and D_4 , respectively, and wherein: the difference between D_4 and D_o is greater than the difference between D_o and D_i ; the number of orifices of the fourth gas-emitting region is less than the number of orifices of each of the inner and outer gas-emitting subregions; and the diameter of the orifices of the inner gas-emitting subregion are substantially equal to the diameter of the orifices of the outer gas-emitting subregion; and greater than the diameter of the orifices of the fourth gas-emitting region.

[0064] The inventive method further comprises a method wherein the soot-producing burner comprises: a burner subassembly which comprises: a back block having a plurality of gas-carrying passages, a face block having a central gas-carrying passage and a plurality of gas-carrying passages surrounding the central gas-carrying passage, a manifold plate between the back block and the face block, said manifold plate comprising a plurality of orifices for providing circumferential equalization of a pressure of a gas flowing through the plurality of gas-carrying passages surrounding the central gas-carrying passage of the face block, and means for forming an assembly of the face block, back block, and manifold plate; a burner subassembly mounting block for attachment to a gas-supplying manifold; and means for mounting the burner subassembly on the burner subassembly mounting block and preferably wherein the gas-carrying passages upstream of the manifold plate have cross-sectional areas, and the orifices of the manifold plate have cross-sectional areas, wherein the cross-sectional areas of the gas-carrying passages upstream of the manifold plate are larger than the cross-sectional areas of the orifices of the manifold plate.

[0065] The invention includes a soot-producing burner comprising: a burner subassembly which comprises: a back block having a plurality of gas-carrying passages, a face block having a central gas-carrying passage and a plurality of gas-carrying passages surrounding the central gas-carrying passage, a manifold plate between the back block and the face block, said manifold plate comprising a plurality of orifices for providing circumferential equalization of a pressure of gas flowing through the plurality of gas-carrying passages surrounding the central gas-carrying passage of the face block, and means for forming an assembly of the face block, back block, and manifold plate; a burner subassembly mounting block for attachment to a gas-supplying manifold; and means for mounting the burner subassembly on the burner subassembly mounting block.

[0066] The invention further includes a soot-producing burner wherein the face block comprises a burner face having first, second, third, and fourth gas-emitting regions, the second region surrounding the first region, the third region surrounding the second region, and the fourth region surrounding the third region, the third gas-emitting region comprises an inner gas-emitting subregion and an outer gas-emitting subregion, the outer gas-emitting subregion of the third gas-emitting region surrounds the inner gas-emitting subregion of the third gas-emitting region, wherein each of (i) the inner gas-emitting subregion, (ii) the outer gas-emitting subregion, and (iii) the fourth gas-emitting region comprises a ring of orifices, said rings having diameters D_i , D_o , and D_4 , respectively, with the difference between D_4 and D_o being greater than the difference between D_o and D_i . The invention further includes a soot-producing burner wherein the face block comprises a burner face having first, second, third, and fourth gas-emitting regions, the second region surrounding the first region, the third region surrounding the second region, and the fourth region surrounding the third region, the third gas-emitting region comprises an inner gas-emitting subregion and an outer gas-emitting subregion, the outer gas-emitting subregion of the third gas-emitting region surrounds the inner gas-emitting subregion of the third gas-emitting region, wherein each of (i) the inner gas-emitting subregion, (ii) the outer gas-emitting subregion, and (iii) the fourth gas-emitting region comprises a ring of orifices, the number of orifices of the fourth gas-emitting region being less than the number of orifices of each of the inner and outer gas-emitting subregions.

[0067] The invention further includes a soot-producing burner wherein the face block comprises a burner face having first, second, third, and fourth gas-emitting regions, the second region surrounding the first region, the third region surrounding the second region, and the fourth region surrounding the third region, the third gas-emitting region comprises an inner gas-emitting subregion and an outer gas-emitting subregion, the outer gas-emitting subregion of the third gas-emitting region surrounds the inner gas-emitting subregion of the third gas-emitting region, wherein each of (i) the inner gas-emitting subregion, (ii) the outer gas-emitting subregion, and (iii) the fourth gas-emitting region comprises a ring of orifices having diameters, the diameter of the orifices of the inner gas-emitting subregion being (a) substantially equal to the diameter of the orifices of the outer gas-emitting subregion and (b) greater than the diameter of the orifices of the fourth gas-emitting region.

Claims

1. An apparatus for the production of silicon dioxide containing soot comprising a burner having a burner face which comprises:

a first gas-emitting region emitting a halide-free silicon-containing material and oxygen;

a second gas-emitting region emitting inert gas, said second gas-emitting region surrounding said first gas-emitting region;
a third gas-emitting region emitting oxygen, said third gas-emitting region surrounding said second gas-emitting region; and
5 a fourth gas-emitting region emitting oxygen and combustible gas, said fourth gas-emitting region surrounding said third gas-emitting region.

2. An apparatus as claimed in claim 1 further comprising a halide-free silicon-containing material and oxygen delivery system connected with said first gas-emitting region.
- 10 3. An apparatus according to claim 1 or 2 wherein for the formation of a silicon dioxide containing preform a plurality of said soot-producing burners are mounted on a gas-supply manifold.
- 15 4. An apparatus according to claim 3 including means for forming the silicon dioxide preform into an optical waveguide.




FIG. 2.




FIG. 3.





FIG. 4.






FIG. 6.






FIG. 7.



THIS PAGE BLANK (USPTO)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) EP 1 254 867 A3

(12) EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
28.01.2004 Bulletin 2004/05

(51) Int Cl.7: C03B 37/014, C03B 19/14,
F23D 14/38

(43) Date of publication A2:
06.11.2002 Bulletin 2002/45

(21) Application number: 02078244.7

(22) Date of filing: 19.12.1995

(84) Designated Contracting States:
DE FR GB IT NL

(30) Priority: 30.12.1994 US 367047

(62) Document number(s) of the earlier application(s) in
accordance with Art. 76 EPC:
99203799.4 / 0 978 491
95944371.4 / 0 800 490

(71) Applicant: Corning Incorporated
Corning, New York 14831 (US)

(72) Inventors:
• Cain, Michael B.
Corning, NY 14831 (US)


• Desorcie, Robert B.
Corning, NY 14831 (US)
• Kiefer, William J.
Horseheads, NY 14845 (US)
• Powers, Dale R.
Painted Post, NY 14870 (US)

(74) Representative: Marchant, James Ian et al
Elkington and Fife,
Prospect House,
8 Pembroke Road
Sevenoaks, Kent TN13 1XR (GB)

(54) Apparatus comprising a burner for producing silicon dioxide soot

(57) A precision burner suitable for oxidizing halide-free, silicon-containing compounds, such as octamethylcyclotetrasiloxane (OMCTS), is provided. The burner may include a subassembly (13) which can be precisely mounted on a burner mounting block (107) through the use of an alignment stub (158), a raised face (162) on the burner mounting block (107) and corresponding recess (160) in the back of the subassembly (13). Disclosed and claimed is an apparatus suitable for producing SiO_2 containing soot, the apparatus comprising a burner having a burner face. The burner's face includes four concentric regions each for emitting a gas: a first central region (36,90) suitable for emitting a mixture of OMCTS and O_2 , a second innershield region (38,92) suitable for emitting N_2 , a third outershield region (40,42,94,96) suitable for emitting O_2 , and a fourth premix region (44,98) suitable for premixing and emitting a mixture of CH_4 and O_2 . The burner provides more efficient use of halide-free silicon-containing raw materials than prior art burners.

FIG. 4.



EP 1 254 867 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 02 07 8244

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with Indicator, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 5 296 012 A (A.J.ANTOS ET AL.) 22 March 1994 (1994-03-22) * column 4, line 66 - column 5, line 5; figures 2,3; example 2 *	1-4	C03B37/014 C03B19/14 F23D14/38
X	US 4 314 837 A (BLANKENSHIP M G) 9 February 1982 (1982-02-09) * figure 2 *	1,2,4	
Y		3	
Y	EP 0 476 218 A (CORNING INC.) 25 March 1992 (1992-03-25) * column 7, line 36 - line 45; figures 2,3 *	3	
X	PATENT ABSTRACTS OF JAPAN vol. 4, no. 50 (C-7), 16 April 1980 (1980-04-16) & JP 55 023068 A (NT&T CORP.), 19 February 1980 (1980-02-19) * abstract *	1,2,4	
X	EP 0 428 068 A (CORNING INC.) 22 May 1991 (1991-05-22) * page 5, line 10 - line 16; figure 1 *	1,2,4	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C03B F23D
X	US 4 417 692 A (ANDREJCO M J ET AL) 29 November 1983 (1983-11-29) * figures 1,6-8 *	1,2,4	
X	EP 0 463 783 A (AT&T CO.) 2 January 1992 (1992-01-02) * figures 3,4 *	1,2	
X	US 4 810 189 A (MIKAMI M ET AL) 7 March 1989 (1989-03-07) * figures 1-4 *	1,4	
		-/--	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 25 November 2003	Examiner Stroud, J
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPC FORM 1503 03 92 (P/C/CI)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 02 07 8244

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 622 340 A (SHIN-ETSU CHEM CO LTD) 2 November 1994 (1994-11-02) * figure 1 *	1,2	
X	US 4 604 118 A (BOCKO P L ET AL) 5 August 1986 (1986-08-05) * figures 2,3 *	1,2	
X	PATENT ABSTRACTS OF JAPAN vol. 013, no. 283 (C-612), 28 June 1989 (1989-06-28) & JP 01 079039 A (NIPPON TELEGR & TELEPH CORP), 24 March 1989 (1989-03-24) * abstract *	1,2	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 25 November 2003	Examiner Stroud, J
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date O : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 82 (P01C01)

ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 02 07 8244

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

25-11-2003

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5296012	A	22-03-1994	AU 662851 B2	14-09-1995
			AU 5250093 A	07-07-1994
			CA 2109474 A1	29-06-1994
			CN 1090258 A ,B	03-08-1994
			DE 69323980 D1	22-04-1999
			DE 69323980 T2	14-10-1999
			EP 0604785 A1	06-07-1994
			JP 6234537 A	23-08-1994
US 4314837	A	09-02-1982	AT 10292 T	15-11-1984
			AU 517154 B2	09-07-1981
			AU 5596180 A	04-09-1980
			BR 8001187 A	04-11-1980
			CA 1136402 A1	30-11-1982
			DE 3069619 D1	20-12-1984
			DK 85880 A ,B,	02-09-1980
			EP 0018068 A1	29-10-1980
			ES 8103386 A1	16-05-1981
			FI 800604 A ,B,	02-09-1980
			IL 59484 A	31-01-1985
			IN 152644 A1	03-03-1984
			JP 1482156 C	27-02-1989
			JP 55116640 A	08-09-1980
			JP 63020772 B	30-04-1988
EP 0476218	A	25-03-1992	NO 800571 A ,B,	02-09-1980
			YU 56880 A1	30-09-1983
			US 5116400 A	26-05-1992
			AU 644155 B2	02-12-1993
			AU 7535691 A	26-03-1992
			CA 2034772 A1	21-03-1992
			DE 69122586 D1	14-11-1996
			DE 69122586 T2	27-02-1997
EP 0476218	A	25-03-1992	EP 0476218 A1	25-03-1992
			JP 2809905 B2	15-10-1998
			JP 4260618 A	16-09-1992
			KR 207309 B1	15-07-1999
			US 5211732 A	18-05-1993
JP 55023068	A	19-02-1980	NONE	
EP 0428068	A	22-05-1991	AT 164369 T	15-04-1998
			AU 647051 B2	17-03-1994
			AU 6596490 A	16-05-1991
			CA 2029590 A1	14-05-1991
			DE 69032175 D1	30-04-1998

EPO FORM P4450

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 02 07 8244

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

25-11-2003

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0428065	A		DE 69032175 T2	09-07-1998
			EP 0428068 A1	22-05-1991
			JP 3287411 B2	04-06-2002
			JP 3295820 A	26-12-1991
			US 5203897 A	20-04-1993
US 4417692	A	29-11-1983	CA 1199533 A1	21-01-1986
			DE 3371291 D1	11-06-1987
			DE 3377791 D1	29-09-1988
			EP 0105926 A1	25-04-1984
			EP 0178032 A1	16-04-1986
			GB 2119079 A ,B	09-11-1983
			WO 8303777 A1	10-11-1983
EP 0463783	A	02-01-1992	US 4474593 A	02-10-1984
			US 5110335 A	05-05-1992
			EP 0463783 A1	02-01-1992
			JP 4228444 A	18-08-1992
US 4810189	A	07-03-1989	JP 1773359 C	14-07-1993
			JP 3009047 B	07-02-1991
			JP 62187135 A	15-08-1987
			BR 8700660 A	15-12-1987
			CA 1265330 A1	06-02-1990
			CN 87100680 A ,B	30-09-1987
			DE 3769179 D1	16-05-1991
			EP 0237183 A1	16-09-1987
			FI 870523 A ,B,	13-08-1987
			IN 169318 A1	28-09-1991
EP 0622340	A	02-11-1994	JP 3007510 B2	07-02-2000
			JP 6305736 A	01-11-1994
			DE 69401028 D1	16-01-1997
			DE 69401028 T2	10-04-1997
			EP 0622340 A1	02-11-1994
US 4604118	A	05-08-1986	AT 73433 T	15-03-1992
			AU 581335 B2	16-02-1989
			AU 6102586 A	19-02-1987
			BR 8603795 A	17-03-1987
			CA 1249305 A1	24-01-1989
			DE 3684204 D1	16-04-1992
			DK 382586 A	14-02-1987
			EP 0213715 A2	11-03-1987
			ES 2000608 A6	01-03-1988
			FI 863275 A ,B,	14-02-1987

EPO FORM P459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 02 07 8244

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

25-11-2003

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4604118	A	IN 167640 A1	24-11-1990
		JP 62041738 A	23-02-1987
		MX 168670 B	03-06-1993
		NO 863248 A	16-02-1987

JP 01079039	A	24-03-1989	NONE

EPO FORM P450

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82